

#### DESCRIPTION

Absolac® 320 is an easy flow standard impact strength, better chemical resistance refrigerator grade. Suitable for Appliances sector.

#### FEATURES

- Refrigerator grade
- Better Chemical Resistance
- Medium Flow

#### APPLICATIONS

- Refrigerator parts
- Deep Freezer

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt flow index 220 °C/10 kg	ISO 1133	gm/10 min	18
Mould Shrinkage	ASTM D955	%	0.3 – 0.5
<b>Mechanical Properties</b>			
Rockwell Hardness	ISO 2039	R-Scale	110
Tensile Strength at yield ( 50 mm /min)	ISO 527	MPa	48
Tensile Strength at yield ( 50 mm /min)	ASTM D 638	Kg/cm2	525
Tensile Modulus ( 1mm / min )	ISO 527	MPa	2600
Tensile Modulus ( 50 mm /min )	ASTM D638	Kg/cm2	26,000
Flexural Strength ( 2mm/min )	ISO 178	MPa	74
Flexural Strength ( 5mm/min )	ASTM D790	Kg/cm2	750
Flexural Modulus ( 2mm / min )	ISO 178	MPa	2600
Flexural Modulus ( 5mm / min )	ASTM D790	Kg/cm2	27,000
Charpy Notched Impact Strength, 23° C	ISO 179	KJ/m2	19
Izod Notched impact strength (1/4" thickness)	ASTM D256	Kg.cm/cm	20
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	96
Vicat Softening Temperature , VST B-50N	ASTM D1525	°C	98
Heat Deflection Temperature ( annealed 80 °C for 4 Hrs , 1.80 MPa)	ASTM D648	°C	94
<b>Other Properties</b>			
Specific gravity	ASTM D792	-	1.04

## Absolac® 320

### Acrylonitrile Butadiene Styrene (ABS)

Processing			
Melt Temp Range		°C	220 - 250
Mold Temp Range		°C	60 - 80
Drying Temperature		°C	80
Drying Time		Hr.	2 - 4

### SUPPLY FORM

Absolac® is delivered in the form of cylindrical pellets. Standard Packaging unit: 25 kg with HDPE laminate paper bag with HMHDPE liner. In dry areas with normal temperature control, Absolac® can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Absolac® absorbs moisture, but this can be removed by drying.

### PRODUCT SAFETY

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

### DISCLAIMER

The above information is provided in good faith and Styrenix is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user. With respect to OEM specific modified grades in terms of pre-coloring, performance enhancement and/or additive packages, the properties may be affected to certain extent. Styrenix makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.