

Absolan® 2150 Styrene Acrylonitrile (SAN)

DESCRIPTION

Absolan 2150 is High Flow, Heat & Chemical resistance grade.

FEATURES

- High Flow Grade

APPLICATIONS

- Ball Pens
- Stationary & Novelty

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt flow index 220 °C/10 kg	ISO 1133	gms / 10 min	>40
Mould Shrinkage	D 955	%	0.3 – 0.6
Mechanical Properties			
Rockwell Hardness	D 785	M-Scale	86
Tensile Strength at yield (5 mm /min)	D 638	Kg/cm2	700
Tensile Modulus (5 mm /min)	D 638	Kg/cm2	47000
Flexural strength (1.3 mm/min)	D 790	Kg/cm2	1150
Flexural modulus (1.3 mm / min)	D 790	Kg/cm2	41500
Izod notched impact strength (at 1/4" thickness)	D 256	Kg cm/cm	1.0
Izod un-notched impact strength (at 1/4" thickness)	D256	Kg cm/cm	16
Thermal Properties			
Vicat Softening Temperature	D 1525	°C	104
Heat Deflection Temperature (annealed 80 °C/ 4Hrs, 1.80 MPa)	D 648	°C	97
Heat Deflection Temperature (annealed 80 °C/ 4Hrs, 0.45 MPa)	D 648	°C	100
Other Properties			
Specific gravity	D 792	-	1.07

Absolan® 2150

Styrene Acrylonitrile (SAN)

Processing

Melt Temp Range	°C	220 – 250
Mold Temp Range	°C	60 – 80
Drying Temperature	°C	80
Drying Time	Hr.	2 – 4

SUPPLY FORM

Absolan® is delivered in the form of cylindrical pellets. Standard Packaging unit: 25 kg with HDPE laminate paper bag with HMHDPE liner .In dry areas with normal temperature control, Absolan® can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Absolan® absorbs moisture, but this can be removed by drying.

PRODUCT SAFETY

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

DISCLAIMER

The above information is provided in good faith and Styrenix is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user. With respect to OEM specific modified grades in terms of pre-coloring, performance enhancement and/or additive packages, the properties may be affected to certain extent. Styrenix makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.