

ENGITECH® B16 909000

Provisional Data Sheet

Compound in PA 6

PRODUCT DESCRIPTION

ENGITECH® B16 909000 is a glass reinforced PA6 compound having excellent mechanical properties, flow behavior and good dimensional stability.

Property	Test Condition	Unit	Standard	Typical value
Mechanical properties (23 °C/50 % r. h.)				
Tensile strength	50 mm/min	MPa	ASTM D638	70
Flexural modulus	2 mm/min	MPa	ASTM D790	4500
Flexural strength	2 mm/min	MPa	ASTM D790	100
Izod impact strength (notched)	23 °C	J/m ²	ASTM D256	55
Thermal properties				
Melting temperature	10 °C/min	°C	ASTM D3418	222
Other properties (23 °C)				
Density		g/cc	ASTM D792	1.35
Filler Content		%	ASTM D5630	30
Processing recommendations				
Drying temperature dry air dryer		°C		80
Drying time dry air dryer		h		3 - 4
Residual moisture content		%	PBI	0.2

USAGE

ENGITECH® B16 909000 is especially suited for the injection molding of general purpose application

STORAGE AND SHELF LIFE

It is recommended to store ENGITECH® B16 909000 compound in dry, dust free sealed conditions and prevent exposure to direct sunlight and/or heat. The storage should not exceed 12 months at 25°C for optimum performance. Higher temperature might reduce storage time considerably.

*The information and recommendations contained herein are believed to be accurate and should only be used as a guide. With respect to this publication and the product related thereto, manufacturer makes no guarantee or warranty of any kind, express or implied and shall not be liable for consequential or incidental losses or damages resulting from use of this publication or handling or use of product, including, health related damages or injuries or infringement of intellectual property rights. The person receiving it shall make his own determination, through proper trials and evaluation about the suitability of the information or product for his particular use.