

ISONYL	Grade	A 66 GF30 BK	Code	180030
	Polymer	Polyamide 66		
	Application	Injection moulding		

30% glass fiber reinforced polyamide 66. Colour black.

Properties	Method	Unit	Value
Physical			
Density at 23°C	ASTM D729	g/cm3	1,36
Mould Shrinkage (%)	INTERNAL	%	0,4
Filler Content (1h/600°C)	ASTM D5630	%	30
Thermal			
Vicat B50	ASTM D1525	°C	250
HDT, A (1.80 MPa)	ASTM D1525	°C	250
Mechanical at 23 °C			
Flexural Modulus (23°C - 2 mm/min)	ASTM D790	MPa	8500
Tensile stress at break (23°C-5 mm/min)	ASTM D638	MPa	180
Tensile elong. at break (23°C-5 mm/min)	ASTM D638	%	3,0
Izod notched impact strength (23°C) ASTM	ASTM D256	J/m	140
Flammability Class			
Flammability class (3,0 mm)	UL94		HB

Regulations compliance

RoHS compliance status: **COMPLIANT**

UL listed file n°:

Water contact approvals.

Food contact status:

Technical documents

Process data for injection moulding:	http://www.sirmax.it/sites/default/files/ISONYL%C2%AE%20Process%20Data.pdf
Material safety datasheet:	http://www.sirmax.it/sites/default/files/ISONYL%C2%AE%20MSDS.pdf

Revision number/date: 0 jan 10

§ Moulding shrinkage is not an intrinsic property of plastics. It also depends on moulding parameters. The values reported have been calculated in the direction parallel to the flow in a 3.0 x 12.7 x 127 mm sample.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

The value above is the representative value of the NP standard and may have deviation. It can only be used for selecting materials and shall not be regarded as a material specification and cannot be used for molding designs. Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of Sirmax. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of Sirmax and/or a design that uses or utilizes Sirmax recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using Sirmax's materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.