

IH830C PMMA, Injection Grade

PROPERTY	CONDITION	UNIT	METHOD	VALUE
OPTICAL PROPERTIES				
Refractive Index	nd	-	ISO 489	1.49
Light Transmittance	3.2mm	%	ISO 13468-1	92
Haze	3.2mm	%	ISO 14782	<0.5
THERMAL PROPERTIES				
Melt Flow Index	230°C/3.8kg	g/10min	ISO 1133	2.0
VICAT Softening Point	B/50	°C	ISO 306	108
Heat Deflection Temperature	1.8MPa	°C	ISO 75	101
Coefficient of Linear Expansion	-	1/°C	ASTM D696	6X10 ⁻⁵
MECHANICAL PROPERTIES				
Charpy Impact Strength	notched	kJ/m ²	ISO 179	1.5
Rockwell Hardness	M scale	-	ISO 2039-2	100
Tensile Strength at Break	5mm/min	MPa	ISO 527	74
Tensile Strain at Break	5mm/min	%	ISO 527	5.0
Tensile Modulus	1mm/min	GPa	ISO 527	2.9
Flexural Strength	2mm/min	MPa	ISO 178	113
Flexural Modulus	2mm/min	GPa	ISO 178	3.0
GENERAL PROPERTIES				
Density	-	g/cm ³	ISO 1183	1.19
Mold Shrinkage	-	%	ASTM D955	0.2-0.6
Water Absorption	24hr	%	ASTM D570	0.3
Flammability UL94	1.5mm	Class	IEC 60695-11-10	HB
RECOMMENDED PROCESSING CONDITIONS				
Predrying Temperature		°C		Max. 90
Predrying Time in Desiccant-Type Drier		hr		3-4
Melt Temperature		°C		220-250
Mold Temperature		°C		50-70

REMARKS : The listed values should be used for reference purpose only.