

# N1 000 UF GY 35 POLYAMIDE (PA-6)



## PRODUCT DESCRIPTION

Nylon 6 Unfilled Grey

## FEATURES

- Excellent Mechanical & Chemical properties
- Color: RAL 7035

## APPLICATIONS

- Electricals
- Automotive
- Furniture

TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
<b>PHYSICAL PROPERTIES</b>			
Density	D-792	g/cc	1.15
<b>MECHANICAL PROPERTIES</b>			
Tensile Strength Break	D-638	MPa	70
Elongation Break	D-638	%	30
Flexural Strength	D-790	MPa	95
Impact Strength (IZOD Notched)	D-256	Kg .cm/cm	7
<b>THERMAL PROPERTIES</b>			
Heat Deflection Temperature – 1.8MPa	D-648	°C	70

## Ravago Manufacturing India Private Limited

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 [www.ravagomi.com](http://www.ravagomi.com)

Rev.No:01

# N1 000 UF GY 35 POLYAMIDE (PA-6)



TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
<b>FLAMMABILITY</b>			
Flame Rating	UL 94	-	HB
Glow Wire Testing	IEC 60695-2-12		NA

<b>INJECTION MOLDING CONDITIONS</b>			
Mold Temperature		°C	60 to 80
Rear Temperature		°C	210 to 220
Middle Temperature		°C	220 to 225
Front Temperature		°C	225 to 235
Nozzle Temperature		°C	235 to 240

### **Drying Conditions**

Material can be dried for 4 hours at 90 - 110°C or until moisture level <0.2%.

### **HANDLING AND STORAGE**

**Handling:** Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

**Storage:** Store in a dry place and away from direct sunlight or heat sources.

### **DISPOSAL CONSIDERATIONS**

**Disposal Method:** It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## **Ravago Manufacturing India Private Limited**

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

+919909901581

Format No: F-QC-20

 [www.ravagomi.com](http://www.ravagomi.com)

Rev.No:01