

N1 230 GF MI BLK POLYAMIDE (PA-6)



PRODUCT DESCRIPTION

Nylon 6 30% Glass Filled Black

FEATURES

- Glass Filled
- Excellent Mechanical & Chemical properties

APPLICATIONS

- Furniture
- Automotive
- Home appliance

TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
PHYSICAL PROPERTIES			
Density	D-792	g/cc	1.36
Ash Content / Reinforcement	D-5630	%	30
MECHANICAL PROPERTIES			
Tensile Strength	D-638	MPa	135
Tensile Modulus	D-638	MPa	6600
Elongation Break	D-638	%	4
Flexural Strength	D-790	MPa	165
Impact Strength (IZOD Notched)	D-256	Kg-Cm/Cm	10
THERMAL PROPERTIES			
Heat Deflection Temperature - 1.8 MPa	D-648	°C	198

Ravago Manufacturing India Private Limited.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

+919909901581

Format No: F-QC-20

www.ravagomi.com

Rev.No:01

N1 230 GF MI BLK POLYAMIDE (PA-6)



TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
FLAMMABILITY			
Flame Rating	UL 94	-	HB
Glow Wire Testing	IEC 60695-2-12	°C	NA

INJECTION MOLDING CONDITIONS			
Mold Temperature		°C	70 to 80
Rear Temperature		°C	220 to 220
Middle Temperature		°C	225 to 230
Front Temperature		°C	230 to 235
Nozzle Temperature		°C	235 to 240

Drying Conditions

Material can be dried for 4 hours at 100 - 110°C or until moisture level <0.2%.

HANDLING AND STORAGE

Handling: Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

Storage: Store in a dry place and away from direct sunlight or heat sources.

NOTE: Possible presence of metallic particles < 0.8 mm.

DISPOSAL CONSIDERATIONS

Disposal Method: It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Manufacturing India Private Limited.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 www.ravagomi.com

Rev.No:01