

# N2 000 UF BLK POLYAMIDE (PA-66)



## PRODUCT DESCRIPTION

Nylon 66 Unfilled Black

## FEATURES

- Excellent Mechanical & Chemical properties
- Good Processing Characteristics

## APPLICATIONS

- Automotive
- Home appliance
- Cable Tie

TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
<b>PHYSICAL PROPERTIES</b>			
Density	D-792	g/cc	1.14
Ash Content / Reinforcement	D-5630	%	NA
<b>MECHANICAL PROPERTIES</b>			
Tensile Strength	D-638	MPa	75
Elongation Break	D-638	%	15
Flexural Strength	D-790	MPa	98
Impact Strength (IZOD Notched)	D-256	kJ/m <sup>2</sup>	7
<b>THERMAL PROPERTIES</b>			
Heat Deflection Temperature - @1.8 MPa	D-648	°C	95
Vicat Softening Temperature @ 50N	D-1525	°C	NA

## Ravago Manufacturing India Private Limited.

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 [www.ravagomi.com](http://www.ravagomi.com)

Rev.No:01

# N2 000 UF BLK POLYAMIDE (PA-66)



TYPICAL PROPERTIES	TEST ASTM	UNIT	Test Values
<b>FLAMMABILITY</b>			
Flame Rating	UL 94	-	HB
Glow Wire Testing	IEC 60695-2-12		NA

<b>INJECTION MOLDING CONDITIONS</b>			
Mold Temperature		°C	70 to 80
Rear Temperature		°C	245 to 255
Middle Temperature		°C	250 to 260
Front Temperature		°C	260 to 270
Nozzle Temperature		°C	270 to 280

### Drying Conditions

Material can be dried for 4 hours at 100 - 110°C or until moisture level <0.2%.

### **HANDLING AND STORAGE**

**Handling:** Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

**Storage:** Store in a dry place and away from direct sunlight or heat sources.

### **DISPOSAL CONSIDERATIONS**

**Disposal Method:** It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## **Ravago Manufacturing India Private Limited.**

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 [www.ravagomi.com](http://www.ravagomi.com)

Rev.No:01