

# PEBAX® MV 3000 SP 01

Polyether block **Pebax® MV 3000 SP 01 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This hydrophilic grade when extruded into either a thin film or laminated on to a substrate offers excellent permeability to moisture vapor while remaining waterproof.

This SP grade is specifically designed for outdoor application that needs excellent weather resistance properties.

## MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	- / 45	MPa	ISO 527-1/-2
Stress at 50% Strain	- / 7	MPa	ISO 527-1/-2
Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, 15s	35 / *	-	ISO 7619-1
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	158 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Water Absorption	28 / *	%	Sim. to ISO 62
Humidity Absorption	1 / *	%	Sim. to ISO 62
Density	1020 / 1020	kg/m <sup>3</sup>	ISO 1183

## MAIN APPLICATIONS:

- Breathable membranes

## PACKAGING:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

## SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

### Processing conditions:

- Cast Film - Typical melt temperature : 240 - 250°C.
- Blown Film - Typical melt temperature : 190 - 210°C.
- Coating - Typical melt temperature : 240 - 250°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 70-80°C.

## PROCESSING

Film Extrusion, Other Extrusion, Calendering, Casting

## DELIVERY FORM

Pellets

## REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

# PEBAX® MV 3000 SP 01

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema  
© 2022 Arkema Inc. All rights reserved.

**pebax.com**

**Arkema Inc. – Technical Polymers**  
900 First Avenue  
King of Prussia, PA 19406  
Tel.: +1 610 205 7000  
Fax: +1 610 205 7497  
[arkema-america.com](http://arkema-america.com)

**PEBAX®**  
**BY ARKEMA**

**Headquarters: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
Tel.: +33 1 49 00 80 80  
Fax: +33 1 49 00 83 96  
[arkema.com](http://arkema.com)