

TECHNICAL DATA SHEET

RILSAMID® AZM 50 BLACK T6LD

POLYAMIDE 12 PELLET

RILSAN® AZM 50 BLACK T6LD is a polyamide 12 compound. This glass fiber reinforced grade is designed for injection molding and is used to produce air brake or automotive fittings & quick connectors, the incorporation of a high amount of glass fibers leading to a very rigid and tough product.

Designation : ISO 16396 - PA12, GF50, M1G1HLR, C16-120

TYPE

PA12-GF50

MAIN APPLICATIONS

- Auto - Fluid Connectors
- Heavy Truck - Air Brake Connectors

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	6	cm³/10min	ISO 1133
Shrinkage, Parallel (t+24h)	0.2	%	ISO 294-4
Shrinkage, Normal (t+24h)	0.7	%	ISO 294-4

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Flexural modulus, 23°C (73°F)	8300 / -	MPa	ISO 178
Tensile modulus, 23°C (73°F), 1 mm/min	12200 / 12000	MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	151 / 143	MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	3.5 / 3.6	%	ISO 527-1/-2
Stress at break, 23°C (73°F), 50 mm/min	152 / 145	MPa	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	4.6 / 4.9	%	ISO 527-1/-2
Charpy unnotched impact strength, 23°C (73°F)	85 / 85	kJ/m2	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	94 / 87	kJ/m2	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 21	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	15 / 15	kJ/m2	ISO 179 1eA
Strain at break, 23°C (73°F), 50 mm/min	4.6 / 4.9	%	ISO 527-1/-2

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

RILSAMID® AZM 50 BLACK T6LD

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3
Thermal degradation temperature, Under air at 10°C/min (1%_wt_Loss)	224	°C	ISO 11358-1
Thermal degradation temperature, Under nitrogen at 10°C/min (1%_wt_Loss)	224	°C	ISO 11358-1

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.2	%	ISO 62
Moisture absorption, After 24h at 23°C (73°F)/Water	0.7	%	ISO 62
Density, 23°C (73°F)	1.47	g/cm³	ISO 1183-1

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

REGIONAL AVAILABILITY

Asia Pacific, Europe, Northern America

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

