

RILSAMID® MA 4411 BLACK

PA12, MHLR, 16-010

Rilsamid® MA 4411 BLACK resin is plasticized and designed for tube extrusion.

Rilsamid® MA 4411 BLACK resin falls into the PA12-HIPHL category according to DIN 73378 (PA12-HIP, EHL, 22-004).

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	14 / *	cm ³ /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	5 / *	kg	-
	11 / *	lb	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 470	MPa	ISO 527-1/-2
	- / 68200	psi	
Yield Stress	- / 25	MPa	ISO 527-1/-2
	- / 3630	psi	
Yield Strain	- / 23	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	63 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 6	kJ/m ²	ISO 179/1eA
	- / 2.85	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	175 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1030 / -	kg/m ³	ISO 1183
	1.03 / -	g/cm ³	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID[®]

MA 4411 BLACK

<p>PROCESSING</p> <p>Profile Extrusion, Other Extrusion</p>	<p>Headquarters:</p> <p>Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com</p> <p>Arkema Inc. – High Performance Polymers</p> <p>900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com</p>
<p>DELIVERY FORM</p> <p>Pellets</p>	
<p>ADDITIVES</p> <p>Plasticizer</p>	
<p>SPECIAL CHARACTERISTICS</p> <p>Heat Stabilized, Light Stabilized</p>	
<p>REGIONAL AVAILABILITY</p> <p>North America, Europe, Asia Pacific, South and Central America, Near East/Africa</p>	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France)
 Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 20-02-2024