

RILSAN®

BMN BLACK TLD

PA11, MHLR, 12-010

Rilsan® BMN BLACK TLD resin is a polyamide 11 produced from a renewable source. This black grade is designed for injection molding.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	36.5 / *	cm ³ /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	2.16 / *	kg	-
	4.76 / *	lb	-
Molding Shrinkage, parallel	1.5 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.5 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	- / 1500	MPa	ISO 527-1/-2
	- / 218000	psi	
Yield Stress	- / 45	MPa	ISO 527-1/-2
	- / 6530	psi	
Yield Strain	- / 6	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	72 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 6	kJ/m ²	ISO 179/1eA
	- / 2.85	ftlb/in ²	
Charpy Notched Impact Strength, -30°C	- / 7	kJ/m ²	ISO 179/1eA
	- / 3.33	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	188 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	50 / *	°C	ISO 75-1/-2
	122 / *	°F	
Temp. of Deflection Under Load, 0.45 MPa	145 / *	°C	ISO 75-1/-2
	293 / *	°F	
Vicat Softening Temperature, 50°C/h 50N	160 / *	°C	ISO 306
	320 / *	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN®

BMN BLACK TLD

Coeff. of Linear Thermal Expansion, parallel	85 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at Thickness h	V-2 / *	class	IEC 60695-11-10
Thickness Tested	3.2 / *	mm	-
	0.1260 / *	in	
Yellow Card available	yes / *	-	-
Oxygen Index	25 / *	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	4 / -	-	IEC 60250
Relative Permittivity, 1MHz	3 / -	-	IEC 60250
Dissipation Factor, 100Hz	598 / -	E-4	IEC 60250
Dissipation Factor, 1MHz	262 / -	E-4	IEC 60250
Volume Resistivity	- / 1E12	Ohm* m	IEC 62631-3-1
Surface Resistivity	* / 1E14	Ohm	IEC 62631-3-2
Dielectric (Electric) Strength	- / 30	kV/mm	IEC 60243-1
	- / 762	kV/in	
Comparative Tracking Index	* / 600	-	IEC 60112
OTHER PROPERTIES			
Water Absorption, 23°C, immersion, equilibrium	1.9 / *	%	ISO 62
Humidity Absorption, 23°C, RH50%, equilibrium	0.8 / *	%	ISO 62
Density	1030 / 1030	kg/m³	ISO 1183
	1.03 / 1.03	g/cm³	

MAIN APPLICATIONS:

- Injected parts

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:


Two years from the delivery. For any use above this limit, please refer to our technical services.

RILSAN[®]


BMN BLACK TLD

DIAGRAMS


VISCOSITY-SHEAR RATE




SHEARSTRESS-SHEAR RATE



DYN. SHEAR MODULUS-TEMPERATURE




STRESS-STRAIN




RILSAN® BMN BLACK TLD


SECANT MODULUS-STRAIN



STRESS-STRAIN (ISOCHRONOUS) 248°F



CREEP MODULUS-TIME 248°F



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 210°C / 230°C / 280°C.
- Mold temperature : 20 - 60°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

RILSAN®

BMN BLACK TLD

PROCESSING Injection Molding	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets	
ADDITIVES Release agent	
SPECIAL CHARACTERISTICS Bio-Based, Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.