

ENSOFT SO-141-45D

ENSOFT-S



Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. Based)
Process Method :	Injection/multi injection molding
Uses :	Industrial applications, automotive, personal care, toys, consumer goods, home&kitchen appliances
Revision Date :	01.06.2013

	Value	Unit	Standard
Physical			
Hardness	45	SHORE D	ISO 868 (3 second)
Density	1,1	gr / cm3	ISO 1183 1-A
Brittleness Point	-55	°C	*
Mechanical			
100% Modulus	8	Mpa	ISO 37, DIN 53504
300% Modulus	10	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	12	Mpa	ISO 37, DIN 53504
Elongation at Break	610	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	115	kN/m	ISO 34-1
Thermal			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	135	°C	*

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India
☎ +919909901581
Format No: F-QC-20



www.ravagomi.com
Rev.No:01

ENSOFT SO-141-45D

ENSOFT-S



Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20



www.ravagomi.com

Rev.No:01

ENSOFT SO-141-45D

ENSOFT-S



Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

Important Notice;

The above results are obtained from the tests conducted in Enplast laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. ENPLAST accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India
☎ +919909901581
Format No: F-QC-20



www.ravagomi.com
Rev.No:01