

Styrenix PS 437

High Impact Polystyrene (HIPS)

DESCRIPTION

Styrenix PS 437 is a high flow, high impact polystyrene with a good heat resistance and a high stiffness.

FEATURES

- High flow HIPS
- Good heat resistance with high stiffness
- Suitable for gas-assisted injection molding process
- Good Toughness

APPLICATIONS

- LCD Back cover, instruments & printer cabinets etc.
- AC Grills, Toys, Computer accessories, Refrigerator components.
- internal parts of vacuum cleaners; refrigerator parts etc.
- Large housing parts, critical & shapely design multicavity parts

Property, Test Condition	Standard	Unit	Typical Values
Rheological Properties			
Melt Volume Rate 200 °C/5 kg	ISO 1133	cm ³ /10 min	8.5
Mechanical Properties			
Izod Notched Impact Strength, 23° C	ISO 180/A	kJ/m ²	12
Charpy Notched Impact Strength, 23 °C	ISO 179	kJ/m ²	15
Charpy Unnotched, 23 °C	ISO 179	kJ/m ²	N
Charpy Unnotched, -30 °C	ISO 179	kJ/m ²	130
Tensile Stress at Yield, 23 °C	ISO 527	MPa	24
Tensile Strain at Yield, 23 °C	ISO 527	%	1.5
Tensile Strain at Break, 23 °C	ISO 527	%	42
Tensile Modulus	ISO 527	MPa	1900
Elongation at Break (MD)	ISO 527	%	38
Flexural Strength	ISO 178	MPa	38
Flexural Modulus	ISO 178	MPa	2000
Hardness, Ball Indentation	ISO 2039-1	MPa	74
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	88
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	96
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	84
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	88
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	100
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 60250	-	2.5
Dissipation Factor (100 Hz)	IEC 60250	10 ⁻⁴	4
Dissipation Factor (1 MHz)	IEC 60250	10 ⁻⁴	4
Dielectric Strength, Short Time, 1.5 mm	IEC 60243-1	kV/mm	155

Styrenix PS 437 High Impact Polystyrene (HIPS)

Relative Permittivity (100 Hz)	IEC 60250	-	2.5
Relative Permittivity (1 MHz)	IEC 60250	-	2.5
Volume Resistivity	IEC 60093	Ohm*m	>1E16
Surface Resistivity	IEC 60093	Ohm	>1E13
Optical Properties			
Specular Gloss, 60°	ASTM D 523	%	45
Other Properties			
Density	ISO 1183	kg/m ³	1050
Water Absorption, Saturated at 23°C	ISO 62		<0.1
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	<0.1
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.6
Melt Temperature Range	ISO 294	°C	180 - 260
Mold Temperature Range	ISO 294	°C	10 - 60
Injection Velocity	ISO 294	mm/s	200

SUPPLY FORM

Styrenix PS 437 is supplied as cylindrical shaped granules. It has to be kept in its original containers in a dry, cool place. Avoid direct exposure to sunlight. Styrenix PS 437 can also be stored in silos.

PROCESSING

Styrenix PS 437 can be processed by any method applicable to polystyrene based plastics, it is best suitable for injection molding and extrusion molding. Recommended processing at temperatures between 180 and 280°C and mold temperatures are between 10 and 60°C. The melt temperature should not exceed 240 °C.

PRODUCT SAFETY

During processing of Styrenix PS resins small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is where five to eight air changes per hour are made. Further information can be found in our Styrenix PS safety data sheets.

DISCLAIMER

The above information is provided in good faith and Styrenix is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user. With respect to OEM specific modified grades in terms of pre-coloring, performance enhancement and/or additive packages, the properties may be affected to certain extent. Styrenix makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.