

## Technical Data Sheet

### • Features

Excellent mechanical properties, Fast cycling, Good demolding properties.

### • Applications

Protective smartphone & pad (jelly) cases, Footwear etc.

### • Properties

Physical Properties	Unit	Test Method	Value
Hardness	Shore A	ASTM D2240	96
Specific Gravity	g/cm <sup>3</sup>	ASTM D792	1.20
100% Modulus	MPa	ASTM D412	14
300% Modulus	MPa	ASTM D412	25
Tensile Strength	MPa	ASTM D412	40
Ultimate Elongation	%	ASTM D412	450
Tear Strength	N/mm	ASTM D624	150

Note: The above values are shown as typical values and should not be used as specifications. Package: 25kg/bag & pellets.

### • Material Preparation

Prior to processing, HD-2395A9 must be dried at 90-100°C for 3-4 hours.

### Injection Molding Guide

Item	Parameter
Nozzle (°C)	210
Metering Zone (°C)	205
Compression Zone (°C)	200
Feeding Zone (°C)	195
Injection Pressure (kg)	90

### • HSE Information

Please take MSDS for reference.



SHANGDONG HUADA CHEMICAL NEW MATERIAL CO., LTD.

The information provided here is for reference only. The user has responsibility to test the material to verify their suitability for the proposed processes, purpose and standards. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. We have no control over another party's use of material, and do not take any responsibility for the another party's behavior. We endeavor to ensure the accuracy and reliability of the opinions, information and data contained in the above documents. But these data do not imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law.