

The background of the slide is a blue-tinted photograph of hikers on a mountain. In the foreground, a hiker is climbing a steep, rocky slope. Another hiker is visible further up the slope, and a third hiker is partially visible in the distance. In the background, a large, snow-capped volcano rises against a clear sky. The overall scene conveys a sense of adventure and outdoor activity.

# **UBE**

**Technical information of UBE NYLON 1030B4**

# UBE NYLON 1030B4 (High viscosity homopolyamide 6)


Basic properties <sup>(1)</sup>	Method	Unit	Value
Melting point	ISO 11357	°C	220
Relative Viscosity <sup>(2)</sup>	UBE Method	-	4.08
Viscosity number <sup>(3)</sup>	ISO 307	ml/g	256
Density	DIN 53479	g.cm <sup>-3</sup>	1.14

<sup>(1)</sup> Measured on base resin. Average values.

<sup>(2)</sup> 96% H<sub>2</sub>SO<sub>4</sub>, 1% polymer concentration.

<sup>(3)</sup> 96% H<sub>2</sub>SO<sub>4</sub>, 0.5% polymer concentration.

# Flow properties of UBE NYLON 1030B4



The contents of here written materials were prepared based on materials, information and data available at the present moment. They may be revised because of new knowledge, information and data without notification. The data described herein are averaged values obtained by specified measurement: they are not guaranteed figures.

UBE does not warrant or guarantee the quality or safety of your finished products, including but not limited to implied warranties of merchantability, fitness for a particular purpose and noninfringement of third party rights or arising from a course of dealing, usage or trade practice even if UBE's products and data herein or any other information proposed by UBE are used to manufacture the finished products. Determination of suitability, merchantability or fitness for a particular purpose of your finished products shall be on your responsibility.

UBE has no liability or legal responsibility for any issues or problems in relation to standards, regulations, laws, intellectual property rights – especially patent rights, etc. derived from any applications of UBE products for your finished products. So it should be fully researched and studied by yourself.

UBE highly recommends to read the Safety Data Sheet "SDS" before using UBE products to ensure your safety.

Do not use UBE products in medical application for the parts involving implanting in human body. Please consult in advance for a medical application or parts in contact with food stuff.

"UBE NYLON" is registered trademark in Japan and other countries.

Copyright of all information in document belongs to UBE Chemicals (Asia) Public Company Limited. Reproduction without UBE's permission is strictly forbidden.